



celplast
metallized products



CERAMIS® CPT-005

SILICON OXIDE-COATED POLYESTER FILM

CPT-005 is an SiO_x-coated PET film with a combination of excellent clarity and outstanding barrier properties. This grade also withstands retorting temperatures up to 135°C. It is ideally suited for retort lidding applications.

Properties	Typical Value	Units	Test Method
Thickness	48	gauge	
Yield	41,800	in ² /lb	
Tensile Strength	230 MD 260 TD	N/mm ²	ISO 527-1-2
Elongation	110 MD 90 TD	%	ISO 527-1-2
Heat Shrinkage	1.3 MD 0.1 TD	%	150°C, 15 min.
Haze	2.5	%	ASTM D1003-92
Static COF	0.9 SiO _x /SiO _x 0.5 PET/PET	-	DIN EN ISO 8295
Oxygen Transmission Rate	0.03 pre-retort 0.04 post-retort @ 121°C, 30 min	cc/100 in ² /d	ASTM D3985-81 @ 23°C, 50%RH Laminate 92g PET / CPT-005 / 80 µm CPP
Water Vapor Transmission Rate	0.05 pre-retort 0.06 post-retort @ 121°C, 30 min	g/100 in ² /d	ASTM F372-78 @ 38°C, 90%RH Laminate 92g PET / CPT-005 / 80 µm CPP

The polyester side is in compliance with the regulation FDA 21 CFR 177.1630; approved for direct food contact. When laminated to an approved substrate, the laminate is compliant with the requirements of EU directive 2002/72/EC.

For more information, visit us at <http://cmp.celplast.com>.

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.

CERAMIS® is a registered trademark of Alcan.