



## **ENVIROMET™ PLA 80 g** **HIGH BARRIER METALLIZED POLY(LACTIC ACID) FILM**

### **Typical Values** **Metal One Side, No Treat Other Side**

A metallized bi-axially oriented PLA film, made from a renewable resource: corn. Good handling and excellent barrier properties. Excellent surface brightness and metal adhesion.

<b>Properties</b>	<b>Typical Value</b>	<b>Units</b>	<b>Test Method</b>
Yield	27,600	in <sup>2</sup> /lb	
Standard Gauge	0.8	mil	
Optical Density	2.0 min.	Macbeth	CMP OD-1
Light Transmission	<1.0	%	
MVTR	0.2	g/100in <sup>2</sup> /24 hr.	ASTM E-398 (100° F, 90% RH)
OTR	0.4	cc/100in <sup>2</sup> /24 hr.	ASTM D-3985 (73.4° F, 50% RH)
Metal Adhesion	400	g/in	CMP MA-1
Ultimate Tensile Strength	8,000 MD 8,000 TD	psi	ASTM D882
Base Film Compostability	Passed	-	ASTM D6400

The non-metallized side is FDA approved for direct food contact. Film-to-film heat seals provide film destruct bonds.

The metallized side is FDA approved for indirect food contact.

For more information, visit us at <http://cmp.celplast.com>.

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.