



## **FOILMET™ 48 g** **METALLIZED POLYESTER FILM**

### **Typical Values**

**Metal One Side, Corona Treat Other Side**

Celplast has developed a met PET film which provides guaranteed superior oxygen and water vapor barrier, lot after lot. A surface or reverse printable biaxially oriented polyester film exhibiting excellent adhesion and bright foil appearance. Consistently good handling properties, heat stability, slip, and high tensile strength for easy lamination. Featuring superior MVTR, OTR, and light barrier properties.

<b>Properties</b>	<b>Typical Value</b>	<b>Units</b>	<b>Test Method</b>
Yield	41,600	in <sup>2</sup> /lb	
Average Thickness	0.48 12	mil µm	
Tensile Strength	25,000 MD 30,000 TD	psi	ASTM D882
Tensile Modulus	530,000 MD 560,000 TD	psi	ASTM D882
Elongation	90 MD 70 TD	%	ASTM D882
Optical Density	2.0	Macbeth	CMP OD-1
Light Transmission	1.0	%	
Coefficient of Friction	0.45 Kinetic 0.55 Static	-	ASTM D1894
MVTR	< 0.04	g/100in <sup>2</sup> /24 hr.	ASTM E398 (100° F, 90% RH)
OTR	< 0.03	cc/100in <sup>2</sup> /24 hr.	ASTM D3985 (73.4° F, 50% RH)
Metal Adhesion	300	g/in	CMP MA-1
Surface Energy on Non-metal Side	54	dyne/cm	ASTM D2578

The polyester side is in compliance with the regulation FDA 21 CFR 177.1630 (f, g, h) and EU Directive 2002/72. The metallized side is FDA approved for indirect food contact.

The information and opinions herein are believed to be true and accurate and presented without guarantee or responsibility on our part. No recommendation for use of our product is intended as a patent infringement. No warranty of any kind with respect to patents held by others is implied or intended.